

Strong 1100

■ Sealer



Recommended system

two coats Strong white 1100 may be applied if surface is extremely porous. Apply two coats of putty Plasma 2200 to assure even and smooth surface.

Application Method : Brush, roller or conventional spray.

Application method

Brush, roller or conventional spray

Application Remarks

- Stir the container thoroughly before use periodically during use.
- Not to be applied at temperature below 5°C

Storage Information

SHELF LIFE : 18 months as well ventilated storage area, a way of direct sun.

Net weight : Printed on plastic containers.

Safety Information

- Do not take internally
- Close container after each use
- Use with adequate ventilation (KEEP OUT REACH OF CHILDREN)

■ The information provided about the product is the result of our own laboratory and practical experience. Since the product is often used under different conditions. We cannot guarantee anything but the quality of the product itself. For more inquiries, please contact the technical office

Strong 1100

■ Sealer



Description

Ready to use acrylic latex based undercoat and sealer for cementous Surface.

Features

Specially formulated to seal porous surfaces with excellent alkali resistance film. It will assure good adhesion and prevent Peeling and flaking.

Uses : As an undercoat for Exterior and Interior use on plaster, dry walls, masonry and concrete surfaces.

Technical Data

Color : white

Appearance : smooth and matt

Theoretical spreading rate: 8.0 - 9.0 sq.m/ Lit per coat, depending on porosity of surface .

film thickness : 35-45 micron (one coat dry)

Drying Time (mixture) : at 25°C and 60% R.H

Superficial dryness time : 30 - 40 minutes

Tack free : 1-2 hours

Recoatibility : 3-4 hours

Application information

Recommended thinner : Tap water.

Surface preparation : Surface should be clean and dry Wash with warm soapy water and rinse with fresh water. Glossy surfaces should be dulled by sanding.

	Thinning	Thinner	Nozzle	Pressure
Spray	10 - 15%	Water	0.3-0.4	3-4
Brush or roller	15-20%	Water	---	---